

Natural Rubber Sheet

Usage for Rubber Gasket, Rubber Washer, Industrial Sheeting, for Flooring (such as power station, electrical switch room), door curtain, isolating sheet, insulation sheet, etc

PHYSICAL PROPERTIES	UNIT	RESULT
Hardness	IRHD	*/- 70
Specific Gravity	GM / CC	1.12-1.2
Tensile Strength	PSI	1200
Elongation at Break	%	250
Air Ageing at 70C for 3 Days		
Change in Hardness (%)	IRHD	+5
Change in Tensile Strength (%)	PSI	-10
Change in Elongation at Break (%)	PSI	-5
Change in M100%		+15

(The above results are tested in accordance to material testing procedure BS903)